

KetaSpire® KT-820 CF20

polyetheretherketone

PRELIMINARY DATA SHEET (data subject to change due to limited production history)

KetaSpire® KT-820 CF20 is a 20% chopped carbon fiber-reinforced polyetheretherketone (PEEK.) The carbon fiber content in the formulation is optimized to provide a balance of strength and stiffness, on one hand, with toughness-related properties, such as impact resistance and elongation at break, on the other. The resin enjoys all the key performance attributes for which PEEK is known. These include resistance to harsh chemical environments, high heat resistance (both short and long term) and excellent fatigue resistance. By virtue of the reduced carbon fiber loading, the resin also offers improved surface

aesthetics and reduced anisotropy over comparable 30% carbon fiber-reinforced formulations.

This resin is a low flow/high viscosity grade and is suitable for use in both injection molding and extrusion fabrication. It can be melt processed using standard thermoplastic melt processing equipment.

Potential application areas for KT-820 CF20 include uses in the oil and gas recovery industry, in chemical processing and in other industrial uses where a balance of part stiffness and toughness is required, such as semiconductor fabrication, automotive, aerospace and healthcare industries.

General

Material Status	<ul style="list-style-type: none"> Limited Distribution 	
Availability	<ul style="list-style-type: none"> Africa & Middle East Asia Pacific Europe 	<ul style="list-style-type: none"> Latin America North America
Filler / Reinforcement	<ul style="list-style-type: none"> Carbon Fiber, 20% Filler by Weight 	
Features	<ul style="list-style-type: none"> Autoclave Sterilizable Chemical Resistant E-beam Sterilizable Ethylene Oxide Sterilizable Fatigue Resistant Flame Retardant Good Dimensional Stability Good Sterilizability Heat Sterilizable 	<ul style="list-style-type: none"> High Heat Resistance High Stiffness High Strength Radiation (Gamma) Resistant Radiation Sterilizable Radiotransparent Steam Resistant Steam Sterilizable
Uses	<ul style="list-style-type: none"> Automotive Applications Connectors Dental Applications Electrical/Electronic Applications Gears Hospital Goods Industrial Applications 	<ul style="list-style-type: none"> Medical Devices Medical/Healthcare Applications Oil/Gas Applications Pump Parts Surgical Instruments Thrust Washer
RoHS Compliance	<ul style="list-style-type: none"> RoHS Compliant 	
Appearance	<ul style="list-style-type: none"> Black 	
Forms	<ul style="list-style-type: none"> Pellets 	
Processing Method	<ul style="list-style-type: none"> Injection Molding Machining 	<ul style="list-style-type: none"> Profile Extrusion

Physical

	Typical Value	Unit	Test method
Density / Specific Gravity	1.37		ASTM D792

KetaSpire® KT-820 CF20

polyetheretherketone

Mechanical	Typical Value	Unit	Test method
Tensile Modulus ¹	15400	MPa	ASTM D638
Tensile Strength	187	MPa	ASTM D638
Tensile Elongation ¹ (Break)	2.7	%	ASTM D638
Flexural Modulus	13800	MPa	ASTM D790
Flexural Strength	299	MPa	ASTM D790

Impact	Typical Value	Unit	Test method
Notched Izod Impact	85	J/m	ASTM D256
Unnotched Izod Impact	690	J/m	ASTM D4812

Thermal	Typical Value	Unit	Test method
Deflection Temperature Under Load 1.8 MPa, Annealed	310	°C	ASTM D648

Fill Analysis	Typical Value	Unit	Test method
Melt Viscosity (400°C, 1000 sec ⁻¹)	700	Pa·s	ASTM D3835

Injection	Typical Value	Unit
Drying Temperature	150	°C
Drying Time	4.0	hr
Rear Temperature	365	°C
Middle Temperature	370	°C
Front Temperature	375	°C
Nozzle Temperature	380	°C
Mold Temperature	175 to 205	°C
Injection Rate	Fast	
Screw Compression Ratio	2.5:1.0 to 3.5:1.0	

Notes

Typical properties: these are not to be construed as specifications.

¹ 5.0 mm/min

www.solvay.com

SpecialtyPolymers.EMEA@solvay.com | Europe, Middle East and Africa

SpecialtyPolymers.Americas@solvay.com | Americas

SpecialtyPolymers.Asia@solvay.com | Asia and Australia

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Solvay Group or their respective owners.

© 2020 Solvay Specialty Polymers. All rights reserved.

